

Brugarolas



Industrial Lubricants



ANTICORROSIVOS



Brugarolas displays a wide range of anticorrosive products that fulfill the strictest requirements in temporary protection for all kind of parts. In this brochure our main products are detailed, products with solvent agents or water repellants that protect humid parts, as well as, waxy film anticorrosives used for long life protection in sea transportation activities.

ANTICORROSIVES WITH SOLVENT BASE AND OILY FILM

RUST KEEPER 555

| Specifications | |
|--|-----------------|
| Film type | Oily, very thin |
| Viscosity at 40°C | 1,5 |
| Flash point, °C | 40 |
| Solvent | YES |
| Water repellent | YES |
| Salt spray chamber (ASTM B117), hours | 48 |
| Humidity cabinet (DIN 50017), cycles | 50 |
| Covering power 25°C (m ² /kg) | -- |
| Thickness, micron | 2,8 |

RUST KEEPER 999-MI

| Specifications | |
|--|-----------------|
| Film type | Oily, very thin |
| Viscosity at 40°C | 5 |
| Flash point, °C | 70 |
| Solvent | YES |
| Water repellent | YES |
| Salt spray chamber (ASTM B117), hours | 90 |
| Humidity cabinet (DIN 50017), cycles | >30 |
| Covering power 25°C (m ² /kg) | 58 |
| Thickness, micron | 7,8 |

RUST KEEPER EXTRA FLUID

| Specifications | |
|--|------|
| Film type | Oily |
| Viscosity at 40°C | 10 |
| Flash point, °C | 68 |
| Solvent | YES |
| Water repellent | NO |
| Salt spray chamber (ASTM B117), hours | 55 |
| Humidity cabinet (DIN 50017), cycles | 50 |
| Covering power 25°C (m ² /kg) | 67 |
| Thickness, micron | 12,7 |





ANTICORROSIVES WITH DISOLVENT BASE AND WAXY FILM

RUST KEEPER 922

| Specifications | |
|--|------|
| Film type | Waxy |
| Viscosity at 40°C | 3 |
| Flash point, °C | 40 |
| Disolvent | YES |
| Water repellent | NO |
| Salt spray chamber (ASTM B117), hours | 70 |
| Humidity cabinet (DIN 50017), cycles | >60 |
| Covering power 25°C (m ² /kg) | 44 |
| Thickness, micron | 7 |

RUST KEEPER 923

| Specifications | |
|--|------|
| Film type | Waxy |
| Viscosity at 40°C | 11 |
| Flash point, °C | 40 |
| Disolvent | YES |
| Water repellent | NO |
| Salt spray chamber (ASTM B117), hours | 165 |
| Humidity cabinet (DIN 50017), cycles | >60 |
| Covering power 25°C (m ² /kg) | 20 |
| Thickness, micron | 23 |

RUST KEEPER 924

| Specifications | |
|--|------------|
| Film type | Waxy |
| Viscosity at 40°C | Semi-paste |
| Flash point, °C | 40 |
| Disolvent | YES |
| Water repellent | NO |
| Salt spray chamber (ASTM B117), hours | 1000 |
| Humidity cabinet (DIN 50017), cycles | >60 |
| Covering power 25°C (m ² /kg) | 9 |
| Thickness, micron | 65 |





ANTICORROSIVES WITHOUT DISOLVENTS

RUST KEEPER 5000

| Specifications | |
|--|------|
| Film type | Oily |
| Viscosity at 40°C | 14 |
| Flash point, °C | 150 |
| Disolvent | NO |
| Water repellent | YES |
| Salt spray chamber (ASTM B117), hours | 40 |
| Humidity cabinet (DIN 50017), cycles | 60 |
| Covering power 25°C (m ² /kg) | 118 |
| Thickness, micron | 10 |

RUST KEEPER S

| Specifications | |
|--|-----------|
| Film type | Oily |
| Emulsion pH at 10% distilled water | 9,4 – 9,6 |
| Acid cutting factor | 1 |
| Disolvent | NO |
| Salt spray chamber test, 20% emulsion, (hours) Water of 5 ^o HF | 50 |
| Salt spray chamber test, 20% emulsion, (hours) Water of 20 ^o HF | 40 |

RUST KEEPER S-M

| Specifications | |
|---|-----------|
| Film type | Oily |
| Viscosity at 40°C | 39 |
| Flash point, °C | 150 |
| Disolvent | NO |
| Emulsion pH at 10% distilled water | 9,1 – 9,6 |
| Acid cutting factor | 1,05 |
| Salt spray chamber test, 20% emulsion, (hours) Water of 5 ^o HF | >24 |
| Refractometer factor | 0,95 |

